

## Production and Utilisation of Coal Combustion Products (CCPs) in Germany in 2004

	Coal		Lignite		
Capacity in MW <sub>th</sub>	76.240		64.311		
Burnt coal, million tonnes	52		173		
CCP	Production	Utilisation	Production	Utilisation	
				Restoration/ Reclamation	Others
	million tonnes	%	million tonnes	%	%
Boiler Slag	1.95	100	---	---	---
Bottom Ash	0.56	94	1.72	87	13
Fly Ash	4.45	99	8.72	96	4
FBC Ash	0.44	100	0.27	87	13
FGD-Gypsum	1.93	100	5.73	13	87*
SDA-Product	0.28	100	---	---	---
Others	< 0.1	100	0,1	0	100
<b>Total</b>	<b>9.71</b>	<b>99</b>	<b>16.54</b>	<b>62</b>	<b>38</b>

\* 34 % of this amount on temporary stockpile (depot)