

Production and Utilisation of Coal Combustion Products (CCPs) in Germany in 2008

	Coal		Lignite		
Capacity in MW _{th}	69,698		64,914		
Burnt coal, million tonnes	46		166		
CCP	Production	Utilisation	Production	Utilisation	
				Restoration/ Reclamation	Others
	million tonnes	%	million tonnes	%	%
Boiler Slag	1.36	100	---	---	---
Bottom Ash	0.49	97	1.58	94	6
Fly Ash	3.92	99	8.67	98	2
FBC Ash	0.32	96	0.40	100	0
FGD-Gypsum	1.70	100	5.20	13	87 ¹⁾
SDA-Product	0.25	97	---	---	---
Total	8.04	99	15.85	70	30

¹⁾ 4 % of this amount on temporary stockpile (depot)